



### DESCRIPTION:

- Combines the extra durability and wet look to stained or uncoated concrete for both interior and exterior applications.
- Water reducible clear 'Wet Look' Sealer is non-yellowing and is low odor.
- When applied to a properly prepared surface is highly resistant to the effects of hot automobile tires.
- Formulated for use on surfaces such as driveways, garage floors, patios, walkways, sidewalks, decks, pavers, unglazed tile, brick and stucco.
- Milky white when applied, but dries to a natural super clear gloss finish.
- Not intended for use over wood, metal, granite, terrazzo, marble surfaces or other natural stone products

### ORDERING:

- Available in 1 gallon cans and 5 gallon buckets.
- Coverage is between 200 to 400 square feet per gallon, per coat, depending on the type of surface and porosity.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
2350 WET LOOK CLEAR SEALER 1G	235001	1G	760428235018	14" x 14" x 8"	4	54 Cases
2350 WET LOOK CLEAR SEALER 5G	235005	5G	760428235056	12" x 12" x 15"	1	36 Cases

### STORAGE & HANDLING:

- **Warning!** If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **KEEP AWAY FROM CHILDREN.**
- **KEEP FROM FREEZING**
- **FIRST AID: In case of skin contact**, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. **For eye contact**, flush immediately with large amounts of water, for at least 15 minutes. **If swallowed**, get medical attention immediately. **If inhalation causes physical discomfort**, move to fresh air. **If discomfort persists** or any breathing difficulty occurs, get medical help.

### PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**
- **Warning! Irritant!** Harmful if swallowed, when tinted, contains ethylene glycol which can cause severe kidney damage when ingested and has been shown to cause birth defects in laboratory animals.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.

# 2350 "WET LOOK" SEALER

PROPERTIES	
Weight per Gallon	8.47 lbs.
Color(s)	Milky (wet) - Clear (dry)
Gloss	High
VOC Content	237.40 G/L (cal.)
Solid Content by Weight	28.9%
Solid Content by Volume	27.2%
Resin	Acrylic, self-crosslinking
Flash Point	None
Dry Time @ 70° F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 1/2 to 1 Hour To Recoat: 4 Hours Foot Traffic: 3 to 4 Hours Vehicle Traffic: 72 Hours Full Cure: 21 Days

## APPLICATION:

- Do not dilute
- Do not apply if the threat of rain is imminent or if the air/surface temperature is expected to be below 50°F within the first 24 hours of application.
- Do not apply in extreme heat of day or in direct sunlight
- Hand stir product thoroughly before application.
- Sealer should be applied in thin multiple coats by brush, roller or spray.
- Spray application should be back rolled for uniform film thickness. Avoid heavy application resulting in runs, ponding, flood-coating or puddling.
- 2 - 3 thin coats are recommended depending on the surface being coated and the gloss desired.
- On pavers, do not exceed two thin coats.
- Some surfaces such as inclined driveways, garages, patios, steps, etc. may require a slip resistant additive for safety. Add Anvil #9102 Talon Grip Slip Resistant Additive to the final coat of 'Wet Look' Sealer.
- This product should not be used in place of a nonskid finish.
- We recommend that a parked car stand on cardboard until full cure.

## DIRECTIONS FOR USE AND SURFACE PREPARATION:

- Do not apply to concrete where hydrostatic pressure is present or over 3 lbs. of moisture per 1000 sq. ft. ASTM F1869-04. Check for high pH, ASTM D4262 specification.
- Surface must be clean, dry, and free of loose or chalking paint and other surface contaminants.
- Proper surface preparation will ensure maximum adhesion and durability, ASTM D4258-83 Specification.
- The surface must be clean and free of all wax, grease, oil, dirt, acid, mildew, release agents and all other surface contaminants.
- Failure to remove grease, oil, soap or other contamination will interfere with adhesion of the 'Wet Look' Sealer.
- To clean surface, scrub with a solution of 1/2 cup of TSP (Trisodium Phosphate) per gallon of clean hot water. Rinse thoroughly with a power washer.
- Glossy painted surfaces must be dulled.
- Unpainted concrete surfaces should be mechanically abraded or acid etched before coating, ASTM D4260 Specification. Use Anvil #1450 Concrete & Masonry Cleaner & Etcher. Rinse area thoroughly and allow to dry COMPLETELY before sealing.
- A properly etched surface will have the feel of 120 grit sandpaper.
- Extremely hard, glossy or alkaline concrete may require stronger acid solutions or repeated etching.
- Concrete should be at least 45 days old to reduce the possibility of the occurrence of efflorescence.

## CLEANUP:

- Clean immediately with warm, soapy water.