



DESCRIPTION:

- Provides superior bridging of the coating over seams and small separations.
- Exceeds performance of similar coatings of this type for adhesion and longevity.
- Its brilliant white finish not only beautifies, it reflects up to 90% of the sun's rays lowering heat buildup and reducing air conditioning costs.
- Stays brighter longer since it contains a fungicide to resist mildew growth on the product film.
- Roofs must have adequate pitch to allow water to run off.

ORDERING:

- Available in 1 gallon cans and 5 gallon buckets.
- Coverage is approximately 60 square feet per gallon, per coat, depending on the type of roof.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
6600 ROOF-TEC ACRYLIC WHITE 1G	660001	1G	760428660018	14" x 14" x 8"	4	54 Cases
6600 ROOF-TEC ACRYLIC WHITE 5G	660005	5G	760428660056	12" x 12" x 15"	1	36 Cases

STORAGE & HANDLING:

- **Warning!** If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **KEEP AWAY FROM CHILDREN.**
- **KEEP FROM FREEZING**
- **FIRST AID: In case of skin contact**, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. **For eye contact**, flush immediately with large amounts of water, for at least 15 minutes. **If swallowed**, get medical attention immediately. **If inhalation causes physical discomfort**, move to fresh air. **If discomfort persists** or any breathing difficulty occurs, get medical help.

PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.**
- **Warning! Irritant!** Harmful if swallowed.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.



WARNING: This product can expose you to chemicals including Titanium Dioxide, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov



WARNING: This product can expose you to chemicals including Diuron, which is known to the State of California to cause birth defects and reproductive harm. For more information go to www.P65Warnings.ca.gov

6600 ROOF-TEC ACRYLIC ELASTOMERIC ROOF COATING

PROPERTIES	
Weight per Gallon	10.6 lbs.
Color(s)	Brilliant White
Gloss	Low Sheen
VOC Content	81 Grams per Liter (cal.)
Solar Reflectance	TBD
Thermal Emittance	TBD
Viscosity	108 KU @ 75° F
Solid Content by Weight	44.9%
Solid Content by Volume	30.0%
Resin	Acrylic Emulsion
Flash Point	None
Elongation	100 %
Dry Time @ 75° F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 1 to 2 Hours To Recoat: 24 Hours

DIRECTIONS FOR USE AND SURFACE PREPARATION

- All surfaces must be clean and free of dirt, dust, rust, mildew and other surface contaminants.
- Remove contaminants by sandblasting, high-pressure water blasting or mechanical methods.
- Rinse with water and let dry completely. Substrate must be dry at time of applying primer and subsequent coating.

SUBSTRATES

METAL ROOFS:

- Remove rust mechanically and prime with Anvil 1606 Rust Inhibitive Universal Primer.
- Replace loose fasteners. Seal seams and old fasteners with Anvil Roof-Tec Caulk & Sealant Brush Grade 1220 and Anvil Roof-Tec Seam Sealing Membrane 9414.
- Allow caulked areas to dry 24 hours. If previously coated, prime with Anvil AquaSeal High Solids 236.

CONCRETE ROOFS:

- Repair holes or any weakened areas with high quality masonry cement.
- Repair cracks with Anvil Roof-Tec Caulk & Sealant Brush Grade 1220
- Prime all areas with Anvil AquaSeal High Solids 236.
- Allow to dry 24 hours.

BUILT-UP ROOFS:

- Remove all loose gravel and clean thoroughly.
- Repair cracks and joints with Anvil Roof-Tec Caulk & Sealant 1220 and Anvil Roof-Tec Seam Sealing Membrane 9414.
- Allow caulked areas to dry 24 hours.
- Apply prime coat of ROOF-TEC 6600, sealing completely all of the gravel.
- Allow to dry 24 hours.

ASPHALT ROOFS:

- Clean surface thoroughly.
- Prime with Anvil AquaSeal High Solids 236. Repair cracks and seams with Anvil Roof-Tec Caulk & Sealant 1220 and Anvil Roof-Tec Seam Sealing Membrane 9414.
- Allow to dry 24 hours.

PREVIOUSLY COATED POLYURETHANE FOAM ROOFS:

- Clean surface thoroughly.
- Prime with Anvil AquaSeal High Solids 236. Repair cracks and joints with Anvil Roof-Tec Caulk & Sealant 1220 and Anvil Roof-Tec Seam Sealing Membrane 9414.
- Allow caulk to dry 24 hours.

WOOD ROOFS (CARIBBEAN ROOF):

- Clean surface thoroughly.
- Prime with Anvil 1606 Rust Inhibitive Universal Primer.
- Repair cracks and seal seams with Anvil Roof-Tec Caulk & Sealant 1220 and Anvil Roof-Tec Seam Sealing Membrane 9414.
- Allow to dry 24 hours.

APPLICATION

- Apply only when temperatures are above 50° F and when humidity is below 95% for the next 24 rain free hours. If the roof is hot or day is windy, apply a mist-spray with water just before application to avoid sealer from drying too fast.
- Do not thin product.
- Apply with roller or airless sprayer.
- Airless pump set at 1,500 to 2,000 psi delivering 1 to 2 gallons per minute using spray tip of .026-.035.
- Allow 24 hours between coats.
- Two or three coats at the rate of 60 sq. ft. per gallon are needed for proper sealing. Apply each coat perpendicular to the first coat.
- Apply at package consistency.

CLEANUP:

- Soap and water